

Devonian Stone of New York Inc.
463 Atwell Hill Road
Windsor, NY 13865
(607) 655-2600

TEST SPECIFICATIONS

General Specifications:

Flexural Strength ASTM C880	2563 psi
Bulk Specific Gravity	2.58
Bulk Specific Gravity (SSD)	2.63
Apparent Specific Gravity	2.72
Absorption (%)	1.9
Compressive Strength	over 19,000 psi

Los Angeles Abrasion Test¹

Test Specification; ASTM C 131 Grading

Test Values: NYSDOT Maximum Allowable Loss - 45%

Test Results: 33.61% Loss

Also tested a 48" x 18" x 2" thick paver supported on four comers with a concentrated load applied at the center. The paver withstood over 3,000 Lbs. before failure occurred.

¹These tests were conducted according to ASTM C 127 Specifications by Atlantic Testing Laboratories, Ltd., Albany New York and Soil & Material Testing, Inc., Binghamton, New York.

Static Coefficient of Friction Test²

Glacier Blue, Honed Finish

<u>Static Coefficient of Friction (SCOF)</u>	<u>Dry</u>	<u>Wet</u>	<u>Specification</u>
As Received	0.7	0.8	> 0.6
Cleaned*	0.7	0.8	> 0.6

Glacier Blue, Flame Finish

<u>Static Coefficient of Friction (SCOF)</u>	<u>Dry</u>	<u>Wet</u>	<u>Specification</u>
As Received	1.0	0.7	> 0.6
Cleaned*	1.0	0.9	> 0.6

*Cleaned with Renovator Cleaner as per test procedure

²The Ceramic Tile Institute requires ceramic surfaces to have a minimum SCOP of 0.6 when tested dry or wet according to ASTM C 1028 to be considered slip resistant. Glacier Blue™ Devonian Sandstone, Honed Finish and Glacier Blue™ Devonian Sandstone, Flame Finish meets this requirement when tested dry or wet. These tests were conducted by ABIC Testing Laboratories, Inc., Fairfield, NY.

Devonian Stone of New York Inc.
463 Atwell Hill Road
Windsor, NY 13865
(607) 655-2600

TEST SPECS

Test results according to ASTM C 127 specifications:

Flexural Strength ASTM C880	2563psi
Bulk Specific Gravity	2.58
Bulk Specific Gravity SSD	2.63
Apparent Specific Gravity	2.72
Absorption %	1.9
Compressive Strength	over 19,000psi

Test Description:	Los Angeles Abrasion Test
Test Specification:	ASTM C 131 Grading
Test Values:	NYSDOT Max Allowable loss 45%
Test Results:	33.61% loss

Also tested 48" x 18" x 2" thick paver supported on four comers with a concentrated load applied at the center. The paver withstood over 3000 lbs. before failure occurred.

These test were conducted according to ASTM C 127 specifications by Atlantic Testing Laboratories, LTD, Albany, NY and Soil & Material Testing, Inc. Binghamton, NY.

Devonian Stone of New York Inc.
463 Atwell Hill Road
Windsor, NY 13865
(607) 655-2600

TEST SPECS

Freeze –Thaw Resistance Testing, ASTM C-1026

ABIC Testing Laboratories, Inc. was authorized to test the Glacier Blue™ Devonian Stone for freeze-thaw resistance according to ASTM C-1026.

* Previously soaked stone: One test cycle consists of 6-8 hours at 0°F followed by soaking 16 hours in water at room temperature.

The Glacier Blue™ Devonian Stone showed no change in appearance after twenty freeze-thaw cycles according to the test procedure in ASTM C-1026.
Sandstone vs. Li

ABIC TESTING LABORATORIES, INC.

**24 Spielman Road
Fairfield, NJ 07004**

**973-227-7060
Fax: 973-227-0172**

To: Devonian Stone of New York
Ms. Peggy Rosenthal

September 19, 2008

From: Leonard Mackowiak

Subject: Freeze –Thaw Resistance Testing, ASTM C-1026
Project No 5209-02

Introduction

ABIC Testing Laboratories, Inc. was authorized to test the following stone for freeze-thaw resistance according to ASTM C-1026.

- Glacier Blue Devonian Stone

Results

Sample Identification Freeze-Thaw Cycles (Stone Appearance)

	<u>5 cycles*</u>	<u>10 Cycles</u>	<u>15 Cycles</u>	<u>20Cycles</u>
Glacier Blue Devonian Stone	No effect	No Effect	No Effect	No Effect

* Previously soaked stone: One test cycle consists of 6-8 hours at 0°F followed by soaking 16 hours in water at room temperature

Discussion

The Glacier Blue Devonian Stone showed no change in appearance after twenty freeze-thaw cycles according to the test procedure in ASTM C-1026

Respectfully submitted,



Leonard Mackowiak
Vice President